



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>7</sup> : <b>C09J 7/02, B24B 37/04, 41/06, H01L 21/68</b>		A1	(11) International Publication Number: <b>WO 00/17284</b>
			(43) International Publication Date: 30 March 2000 (30.03.00)
(21) International Application Number: PCT/JP99/04662		(74) Agent: YAMAMOTO, Shusaku; Crystal Tower, 15th floor, 2-27, Shiromi 1-chome, Chuo-ku, Osaka-shi, Osaka 540-6015 (JP).	
(22) International Filing Date: 27 August 1999 (27.08.99)			
(30) Priority Data: 10/263751 17 September 1998 (17.09.98) JP		(81) Designated States: KR, SG, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(71) Applicant (for all designated States except US): NITTA CORPORATION [JP/JP]; 4-26, Sakuragawa 4-chome, Naniwa-ku, Osaka-shi, Osaka 556-0022 (JP).		<b>Published</b> <i>With international search report.          Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(72) Inventors; and (75) Inventors/Applicants (for US only): TANI, Naoyuki [JP/JP]; Nitta Corporation Nara Factory, 172, Ikezawa-cho, Yamatokooryama-shi, Nara 639-1085 (JP). KASAZAKI, Toshiaki [JP/JP]; Nitta Corporation Nara Factory, 172, Ikezawa-cho, Yamatokooryama-shi, Nara 639-1085 (JP). KAWAHARA, Shinichiro [JP/JP]; Nitta Corporation Nara Factory, 172, Ikezawa-cho, Yamatokooryama-shi, Nara 639-1085 (JP). ANDO, Takashi [JP/JP]; Nitta Corporation Nara Factory, 172, Ikezawa-cho, Yamatokooryama-shi, Nara 639-1085 (JP). YAMAMOTO, Masayoshi [JP/JP]; Nitta Corporation Nara Factory, 172, Ikezawa-cho, Yamatokooryama-shi, Nara 639-1085 (JP).			
(54) Title: WORKPIECE RETAINER AND METHOD FOR ATTACHING/DETACHING WORKPIECE BY USING THE SAME			
(57) Abstract			
<p>A workpiece retainer includes an adhesive composition containing a pressure-sensitive adhesive and a side-chain crystallizable polymer so that the side-chain crystallizable polymer is present in an amount of about 1 % to about 30 % by weight based on the adhesive composition. The side-chain crystallizable polymer includes as a main component thereof an acrylic acid ester and/or methacrylic acid ester which has a straight-chain alkyl group including 16 or more carbon atoms as a side chain.</p>			